



# Standard Specification paragraphs:

## Bona Craft Oil 2K + Bona Traffic HD / AS / Bona Traffic / Traffic Natural

The undernoted paragraphs are designed to provide a starting point for the specification of Bona finishes for timber flooring. Information in **blue** should be selected as a choice depending upon the required finish. Contractors should be encouraged to obtain product data and SDS information *in addition* to these paragraphs.

### Preparation

The surface which is to be treated must be sanded to bare timber and free from contamination. It should be flat, level and free from sanding marks – in accordance with industry standards. The final sanding should be completed using a rotary sanding method to a maximum P120 grit; oversanding the flooring will result in the oil not penetrating into the timber. NB. All joints / holes are to be filled with **Bona Mix&Fill**, or similar compatible filler. The floor should be thoroughly cleaned to remove all residual sanding dust prior to application.

For a more intense and uniform colouration, the wood can be water popped prior to applying oil. After sanding is complete dampen the floor evenly using water with a mop, cloth or spray. The floor must dry **overnight** to ensure adhesion of **Bona Craft Oil 2K** is not adversely affected.

### Application

Apply a single application of **Bona Craft Oil 2K** as detailed in the product literature. Additional oil may be added as required during the application process to ensure that an even coverage is obtained. It is important that the application instructions are followed carefully and that all excess oil is removed from the floor.

### **Bona Traffic HD / Traffic HD Anti-Slip / Traffic / Traffic Natural**

Let the floor dry for a minimum 8 hours (12 hours for coloured oil). A longer drying time may be necessary on tropical wood species and/or under unfavourable climatic conditions. To check that the surface is dry, rub with a cotton cloth or paper towel. If the cloth picks up material / colour from the surface then it is not dry. Do not apply finishes until the surface is **fully dry**. Adhesion of the finish coats will be affected if the 2K Oil is not dry.

Vacuum to remove dust, etc. from the surface.

Apply 2 applications of **Bona Traffic HD / HD Anti-Slip / Traffic / Traffic Natural** as detailed in the product datasheet. Gently cut back the floor between coats to remove any slight grain raise. It is important to only use a Bona Scrad Pad system, grit 150 or finer, for this purpose.

Drying time – approx. 2 - 3 hours per coat at 20° C / 60% RH

The sanding, the properties of the timber and application process control the appearance and final colour of a floor. These features can only be evaluated after the system has been completed. It is important to note that marks, colour differences, uneven colouring, etc. are **not** product faults or product related. If unsure as to the condition of the floor or the potential final appearance it is recommended that a trial area of the proposed system be prepared and evaluated prior to the floor being finished.



Phone 1300 882 806