



Standard Specification paragraphs:

Bona DriFast Stain

The undernoted paragraphs are designed to provide a starting point for the specification of Bona finishes for timber flooring. Information in **blue** should be selected as a choice depending upon the timber species to be coated or to obtain different wear / appearance values. Contractors should be encouraged to obtain product data and SDS information *in addition* to these paragraphs.

Preparation

The surface which is to be treated must be sanded to bare timber and free from contamination. It should be flat, level and free from sanding marks – in accordance with industry standards. The final sanding should be completed using a rotary sanding method using a maximum P100 grit for hardwoods or P120 grit for softwood timbers. NB. All joints / holes are to be filled with **Bona Mix&Fill**, or similar compatible filler. The floor should be cleaned to remove all residual sanding dust by vacuuming and a tack mop prior to application.

Application

Stain

Apply a single application of **Bona DriFast Stain**, (**insert colour choice**), by hand or using a buffing machine as detailed in the product literature. Do not apply multiple applications.

Bona DriFast Stains dry in approx. 2 hours with the following exceptions:-

White - 6 hours

Ebony, Spice Brown, Cocoa – 12 to 18 hours

The drying times noted are indicative of the minimum time which the stain must be left at at 20°C / 60% RH. Where colour mixes are made the stain must be left to dry for the longest drying period of the colours used. Adverse site conditions i.e. low temperatures, high humidity, poor ventilation, etc. will extend drying times.

Bona DriFast stain must be overcoated with the specified Bona finish within 48 hours of application.

Primer

All colours except Grey, Birch and White

1 coat of **Bona Intense** applied using a Bona Roller or applicator. A coverage rate of 8 m² / litre should be observed.

Grey, Birch, White / mixed colours containing White

1 coat of **Bona Classic** applied using a Bona Roller or applicator. A coverage rate of 8 m² / litre should be observed.

Drying time for Bona Primers – approx. 1.5 - 2 hours per coat at 20°C / 60% RH

Bona[®]

Phone 1300 882 806

Finish

All colours except Grey, Birch and White

2 / 3 coats of **Bona Finish** applied using a Bona Roller or applicator. A coverage rate of 8 – 10 m² / litre should be observed.

Grey, Birch, White / mixed colours containing White

2 / 3 coats of **Bona Traffic HD / Traffic HD Anti Slip / Traffic / Traffic Natural** applied using a Bona Roller or applicator. A coverage rate of 8 – 10 m² / litre should be observed.

NB. If Bona Intense or Mega are used over Grey, Birch, White and mixed colours containing White the possibility exists of the colours appearing vaguely yellowed.

Inter-coat preparation

Ensure that the coating has thoroughly dried before sanding. The **Bona Scrad** system, sanding disc / screen or abrasive grade should be used for the sanding; 150 grit or finer. The floor should be thoroughly cleaned to remove all residual sanding dust prior to further applications of finish being made.

When applications of finish are made within 24 hours of the previous application no inter-coat sanding is required. It is recommended that the finish is lightly abraded prior to the final application with all specifications.

All coating operations should be made with consideration being given to the prevailing weather conditions and site conditions in accordance with the product label and accepted good practice.

Note

The advice noted above regarding the appropriate primers for the specified colours is designed to provide the best final appearance for the floor. Similarly the specification of the top coat finish is also important and the advice noted should be followed.

Appropriate specification paragraphs for the application of the various Bona finishes may be found in the respective documents in the Specification section within the Professionals tab at www.bona.com.au

Bona[®]

Phone 1300 882 806