

Standard Specification paragraphs:

Bona R410

The undernoted paragraphs are designed to provide a starting point for the specification of Bona products for timber flooring. Contractors should be encouraged to obtain product data and SDS information *in addition* to these paragraphs.

Preparation

The substrate must be even, dry to the touch, clean, free from cracks and physically sound. It should also be slightly textured. If necessary it should be professionally prepared for laying.

Bona R410 should be mixed as detailed on the packaging and used within 20 minutes.

Application

Moisture barrier up to 90% RH: 1 application x R410 + R848T or R850T

Moisture barrier up to 95% RH: 2 applications x R410 + R848T or R850T

An even application should be made using a 6 mm nap roller and / or brush to achieve an application rate of 4 m² / kg. If 2 applications of Bona R410 are made these should be in alternate directions at 90° to each other to ensure that complete coverage is achieved.

NB At least 12 hours must elapse before the flooring is installed.

Measurement of the moisture content of the flooring should be carried out prior to application. Assessment of the suitability and selection of a treatment schedule, as detailed above, is the responsibility of the flooring contractor. A higher specification should be used where doubt remains regarding the moisture content of the floor.

Note to specifiers

It is usually not possible when specifying moisture barriers to know the moisture content of the substrate at the time of installation. It is important however that the correct specification is used to ensure optimum performance.

It is suggested that the paragraphs as noted above will ensure that the correct decisions are made with regard to the contractor choosing the appropriate application.



Bona[®]

Phone 1300 882 806