



Bona[®]

Phone 1300 882 806

Standard Specification paragraphs:

Bona Sportive

The undernoted paragraphs are designed to provide a starting point for the specification of Bona finishes for timber flooring. Information in **blue** should be selected as a choice depending upon the timber species to be coated or to obtain different wear / appearance values. Contractors should be encouraged to obtain product data and SDS information *in addition* to these paragraphs.

Preparation

Bare timber coating

The surface to be coated is to be sanded to bare timber and free from contamination. It should be flat, level and free from sanding marks – in accordance with industry standards. Use the **Bona Scrad** system, sanding disc, screen or abrasive for the final sanding, minimum P120 grit. The floor should be thoroughly cleaned to remove all residual sanding dust by vacuuming and a tack mop prior to application.

Application

Primer

1 coat of **Bona Sportive Primer** applied using a Bona Roller or applicator.

Coverage rate 8 m² / litre

Drying time; approx. 1.5 - 2 hours at 20° C / 60% RH

Finish

2 / 3 coats of **Bona Sportive Finish**, (**insert sheen choice – Gloss / Matt**), applied using a Bona Roller or applicator. A coverage rate of 8 – 10 m² / litre should be observed.

Drying time – approx. 2.5 - 3 hours per coat at 20°C / 60% RH

Line marking

After the first application of Bona Sportive Finish the floor should be abraded to provide a physical key for the line marking paint – see Inter-coat preparation. Mark out the courts as directed using high quality low tack masking tape. Press the tape down firmly to prevent paint creep. Apply Bona Sportive Paint in the appropriate colour using a brush or roller; remove the tape as soon as is practical after the paint application.

Inter-coat preparation

Ensure that the coating has thoroughly dried before sanding. The **Bona Scrad** system, sanding disc / screen or abrasive should be used for the sanding; 150 grit or finer. The floor should be thoroughly cleaned to remove all residual sanding dust prior to further applications of finish being made.

When applications of finish are made within 24 hours of the previous application no inter-coat sanding is required. It is recommended that the finish is lightly abraded prior to the final application with all specifications. Sportive Paint should be lightly abraded using the Bona Scrad system before coating.

All coating operations should be made with consideration being given to the prevailing weather conditions and site conditions in accordance with the product label and accepted good practice.

Australian Specification sheet only – December 2018