



# BONA DRIFAST SEALER

Bona DriFast Sealer is a quick drying, polyurethane sanding sealer designed to penetrate and seal bare sanded timber. It is compatible with Bona water based finishes.

- Easy application
- Penetrates and seals the wood
- Fast drying: 1 ½ - 2 hours
- Rapid hardness development
- Sands easily

## Technical data

Type of finish:	Oil modified primer
Solids content:	Approx. 37%
VOC / Flashpoint:	550 g / litre - 39° C
Drying time:	1.5 – 2* hours * Minimum time under normal climate conditions, 20° C / 60% R.H. with reasonable ventilation. High humidity and low temperatures will extend drying times.
Application tools:	May include brush, cut in pad, lambswool applicator and 5 mm roller N.B. Bona DriFast Sealer contains drying oils. Due to the risk of self-ignition used cloths, rags or similar must be place in water or sealed metal containers immediately after use.
Application rate:	15 – 17 m <sup>2</sup> / Lt depending upon the application method and the coated surface
Safety:	Classified (see Safety Data Sheet)
Cleaning:	Tools should be cleaned in Mineral Spirits (White Spirit) immediately after application
Shelf life:	2 years from production date in unopened original container
Storage / Transport:	The temperature must not fall below + 5° C or exceed 25° C during storage and transport Keep containers closed when not in use.
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations
Pack size:	3.8 Litres only

## Preparation

Ensure the floor is acclimatized to its end-use environment, well sanded, dry and free from sanding dust, oil, wax and other contamination. Rotary sanding, grit 120, should be used for the final sanding process .

Allow Bona DriFast Sealer to reach room temperature and stir thoroughly before use.

Optimal application conditions are between 18 - 25°C and 40 - 60% relative air humidity. High temperatures and / or low humidity will shorten the drying time whilst low temperatures and / or high humidity will lengthen the drying time.

**Minimum temperature for use is 13°C.**

**Bona®**

Phone 1300 882 806

## Treatment schedule

### Untreated wood:

- 1 x Bona DriFast Sealer  
Light sanding
- 2 x Bona water based finish

Bona DriFast Sealer should not be used as the final treatment for timber floors

**NB.** The standard specification for the application of finishes on to a floor sanded back to bare timber is a single application of a Bona primer followed by 2 applications of the same Bona top coat. Where Bona products have been used outside of the specifications noted within the product literature Bona can take **no responsibility** for site related issues or the performance of supplied products.

## Application

1. Apply DriFast Sealer evenly using a 5 mm roller or lambswool applicator. Apply with a smooth motion alternately across and finishing with the grain avoiding accumulations of product. Care should be taken to achieve a uniform level of timber saturation to avoid colour variation. Always maintain a 'wet edge' to avoid overlaps. NB. Observe the application rate. When applied too thickly DriFast Sealer will take longer to dry and there is an increased chance of seeing application marks.
2. When dry, approx. 1.5 – 2\* hours, DriFast Sealer must be abraded thoroughly and evenly throughout the floor area. It is recommended that a Bona Scrad pad or a worn 220 screen be used for this. It is important to move lightly and evenly across the floor taking care not to 'sand through' the finish film.
3. Remove all dust using a vacuum and tack the floor. This may be done either with White spirits or water. Allow the surface to dry.
4. Apply 2 coats of a Bona water based finish.

### Additional information

Very dense timber species, such as Ironbark, may be difficult to coat using Bona DriFast Sealer as penetration into the timber is minimal in heartwood sections. This may lead to the finish being sanded through when preparation is carried out prior to the application of the topcoats. A Bona water based primer should be used as an alternative primer coat.

Natural oils found in and around knots in species with a high natural oil content, e.g. Cypress Pine, may interfere with the drying process of Bona DriFast Sealer. This is rare but if this occurs remove the product from over the knots and continue to prepare and coat the floor with a Bona water based finish.

Bona DriFast Sealer is not recommended for use as a primer with Bona DriFast stain or other similar materials.

## Important notes

The information provided is prepared to the best of our current knowledge and makes no claim to be complete. The User is responsible for establishing that the product and recommendations herein are fit for the designated purpose, wood type and present situation before use. Bona can only guarantee the delivered product. A professional and thereby successful application of the product is beyond our control. If in doubt make a preliminary test. The User is required to read and understand all information contained on package labels and safety data sheets before using this product.

**Bona**<sup>®</sup>

Phone 1300 882 806